

Grain Boundary Diffusion of Atomic Oxygen in Ni and Ni-Cr Binary Alloy Using Ab-initio Calculation Method

Jong Jin Kim, Sang Hoon Shin, Jeong Seok Park, Ji Hyun Kim*

Ulsan National Institute of Science and Technology (UNIST)

100 Banyeon-ri, Eonyang-eup, Ulju-gun, Ulsan Metropolitan City 689-798, Republic of Korea

*Corresponding author: kimjh@unist.ac.kr

1. Introduction

Nickel and nickel base alloys have been widely used as structural materials in nuclear systems because they have good mechanical properties at high temperature, high pressure and corrosion resistance in oxidizing environment. Recently, however, these materials have shown to be suffered from the environment-assist cracking (EAC) such as primary water stress corrosion crack (PWSCC) in pressurized water reactor environments. SCC is a cracking phenomena because of a process involving conjoint corrosion and strain of a metal due to residual or applied stressed within the susceptible environment and it growth along the grain boundary.

To reveal the major mechanism of SCC have done many experiments and have a lot of arguments with some possible ways to explain the corrosion process and many experts try to find the method to mitigate or prevent it.

There are many opinions such as Oxide rupture[1,2], accumulation of critical crack tip strain[3,4] or hydrogen induced cracking[5], but nothing can explain the mechanism clearly and the experiments of SCC usually take a lot of times, have difficulty to make specific environment like primary water in nuclear power plants and the corrosion takes place in tiny localized area, so it is hard to clearly defined.

Meanwhile, according to the increase in the computer calculation speed, atomistic modeling and simulation method has been receiving much attention as a method to evaluate the mechanical properties, thermodynamics and kinetics characteristics of metals and alloys.

Very recently, modeling and simulation studies have been performed to understand the fundamental mechanism of nickel and nickel base alloy corrosion (oxidation) process in high temperature water.

For pure nickel, S. Gruchet et al [6] evaluated diffusion of oxygen in nickel by the variable charge molecular dynamics, and Goerge A. Young et al [7] and E H Megchiche [8] evaluated the diffusion of oxygen in nickel using the ab-initio (first-principle) calculation.. But still it is not enough to understanding the corrosion behavior and to prove the accuracy of the computational results.

The purpose of this work is to understand the oxidation behavior of nickel base alloys through the simulation of diffusion processes of oxygen in nickel and nickel-chromium binary alloy

2. Calculation method

Ab-initio calculation solves the Shrödinger equation with no experimental data. The calculations are performed by Vinena Ab-initio Simulation package (VASP) developed at the Institute für Materialphysik of the Universität Wien [11,12]. The calculation get the total energies, forces, and energy profiles using Density Function Theory [13,14] with spin-polarization concerning, which calculation with the generalized gradient approximation(GGA) [15,16] and Projected-augmented wave(PAW) method[17,18]. The GGA is used with the exchange-correlation functional of Perdew and Wang(PW91)[19] for all calculation.

2.1 Modeling Intergranular Diffusion

Because the SCC is an Intergranular cracking, take $\Sigma 3$ and $\Sigma 5$ twin grainboundaries in Nickel model to prove the oxygen diffusion behavior difference as the grain boundary type. Fig 1. Shows the geometry of $\Sigma 3$ and $\Sigma 5$ grainboundary which used in this calculation. Green balls represent the nickel atoms and pink ball is atomic oxygen.




Fig 1. Grain boundary supercell

For the saddle point corresponding to the migration of the atomic oxygen, the minimum energy pathways was

obtained by using the nudged elastic band(NEB) method with 5 images and the lattice relaxation task is performed by using a conjugate-gradient algorithm and all ions is allowed to relax while the supercell volume keep constant and shape could change.

2.2 Diffusion Pathway

Fig 2. Shows the possible diffusion pathway of oxygen in nickel. Oxygen diffuses from octahedral site to octahedral site directly(O-O, A), or step by tetrahedral site(O-T-O, B)




Fig 2. Calculation supercell (O-O(A), O-T-O(B))

The supercell contains 32 nickel atoms and 1 oxygen and to describe the Alloy 600 Ni-base alloy(Chemical composition : 72%Ni, 15%Cr wt%), 28Nickel + 4 Chromium supercell was used for Ni-Cr binary alloy

3. Summary

This work was focused on the prediction oxygen diffusion behavior in pure nickel in order to understand the fundamental oxidation behavior in nickel metals and nickel base alloys. The VASP calculation package was used for ab-initio calculation. The results of activation energies for the oxygen diffusion in nickel and nickel chromium binary alloy and its difference between diffusion path will be mentioned. Also diffusivity of oxygen along $\Sigma 3$, $\Sigma 5$ grain boundary in nickel and it will be helpful to understand the oxygen behavior in nickel.

REFERENCES

- [1] Vermilyea, D.A. in stress corrosion cracking and hydrogen embrittlement of iron base alloys; Unieux-Firminy France pp 208-217 1977
- [2] Ford, F. P. Environment induced cracking of metals. Kohler, Wi: NACE 1988
- [3] Hall, M.M and D.M. Symons. In Chemistry and Electrochemistry of Corrosion and SCC. New Orleans, TMS 2001
- [4] Hall, M.M. EPRI workshop on Alloy 600. 1997, FL

- [5] van Leewen, Reviews on Coatings and Corrosion 1979
- [6] S.Garruchet, O. Politano, P.Arnooux, V.Vignal Solid State Communications 439-442 vol 150 2010,
- [7] George A. Young et al proceeding of the 12th International Conference of EDMNPS-Water Reactor 2005.
- [8] EH Megchiche, M Amarouche and C Mijoule J. Phys Con Mat vol 19 2007
- [9] D.I. Thomson, V. Heine et al. Philosophical Magazine Letters vol 76 no.4 281-287 1997
- [10] S.Ogata, H. Kitagawa et al. Computational Materials Science 7 271-278 1998
- [11] Kresse G and Hafner L Phys. Rev. B vol 47 558 1993
- [12] Kresse G and Furthmuller F. Phys. Rev B 54 11169 1996
- [13] Hohenberg. P. and W. Kohn, Phys. Rev. 136 1964
- [14] Kohn, W. and L.J. Sham, Phys. Rev. 140 1965
- [15] Wnag, Y. and J.P. Perdew, Phys. Rev. B, 54 1991
- [16] Perdew. J.P. and Y. Wang, Phys. Rev. B, 45 1992
- [17] Kresse G and Joubert D Phys. Rev. B 59 1999
- [18] P.E. Blöchl Phys. Rev. B 50, 17, 953 1994
- [19] Perdew J P and Wang Y Phys. Rev. B 46 1992